

# STONESET

## MOISTURE SENSITIVE STONE TILE ADHESIVE



### **DESCRIPTION:**

**RLA STONESET** is a premium grade, rapid setting, polymer-modified tile adhesive designed for fixing moisture sensitive stone, and for general applications requiring fast turnaround times. The rapid setting properties of Stonest allow the grouting application to be conducted shortly after fixing tiles

### **FEATURES & BENEFITS:**

- Rapid setting for fast turn around times
- Excellent non slump and flexible properties
- Economical
- Suitable for use over green screeds and concrete
- C2FTES1 Classification

### **USES:**

- Floor and wall tiling to internal and external areas
- Internal and external wet areas
- Fixing porcelain and vitrified tiles, terrazzo, mosaics and Class A moisture sensitive natural stone
- Large format tile installations
- General tiling applications requiring fast turnaround times
- Immersed areas - pools, spas and water features

### **SUBSTRATES:**

- Concrete
- Screed
- Render
- Compressed fibre cement sheeting
- Ceramic tile underlay
- Plasterboard
- Acoustic underlay
- RLA wet area membranes

### **SURFACE PREPARATION:**

- Ensure all surfaces are clean, sound, dry, and free from dirt, dust, oil, grease, wax residues, curing compounds, release agents, paints, sharp protruding objects and all other loose and contaminating materials that could compromise the adhesion of the overlaid tiling system.
- All surfaces and substrates to be fit for purpose for their intended use and installed as per manufacturers recommendations and relevant building codes enforced at the time of installation
- Ensure all concrete slabs are allowed to cure for at least seven days, have a wood float finish, and a minimum compressive strength of 20MPa.
- Steel-trowelled, burnished and dense concrete surfaces must be mechanically abraded to roughen surfaces and provide a key before commencing tiling. Alternatively, surfaces can be primed with [RLA NON POROUS PRIMER](#)
- Rendered and screeded surfaces must be allowed to cure for at least 24 hours before commencing tiling.
- Existing tiled surfaces must be well bonded, sound and secure. Surface of tiles to be mechanically abraded/roughened to remove at least 80% of the tile glaze for direct fixing. Alternatively, prime tiled surfaces with [RLA NON POROUS PRIMER](#)

### **PRIMING:**

Highly porous and non-porous surfaces to be primed before installation of Stoneset

### **POROUS/ABSORBENT SURFACES:**

- Apply [RLA POROUS PRIMER](#) by brush or roller at a minimum coverage of 1litre/8m<sup>2</sup> per coat to the substrate and allow to dry

### **NON POROUS/NON ABSORBENT SURFACES**

- Apply [RLA NON POROUS PRIMER](#) by brush or roller at a minimum coverage of 1litre/10m<sup>2</sup> to the substrate and allow to dry

**NOTE:** Refer to RLA primer data sheets for specific application and coverage details

**MIXING:**

- The mixing ratio of Stoneset is 5 litres of water per 20kg bag.
- Pour 5 litres of clean water into a clean pail and gradually add the Stoneset while mixing continuously using an electric stirrer with paddle attachment until a smooth, lump-free consistency is obtained.
- Always add powder to the liquid.
- Allow the mix to stand for 3 minutes and re-stir before applying the adhesive onto the substrate

**APPLICATION:**

- All preparation and tiling should be carried out in accordance with AS 3958: 2023 – Installation of Ceramic and Stone Tiles
- Once the surface has been suitably prepared, apply the adhesive onto the substrate using an appropriately sized notched trowel for the tile size
- For tiles larger than 300 x 300mm back-butter the tiles in addition to notching the floor
- With Clip systems use a 12,15 or 20mm notch and back butter the tile to ensure coverage complies with the standard
- Stoneset should be applied onto the substrate at a rate of 1m<sup>2</sup> at time. Application rates greater than this can result in the adhesive skinning before the tiles are laid
- Once the adhesive skins, do not lay tiles into it, remove and re-apply fresh adhesive.
- When placing the tiles, press them into the wet bed of adhesive by using a sliding action. Ensure no voids occur and full coverage of adhesive is under the tiles.
- For tiles with lugs, grooves or uneven backing it may be required to butter the back of the tile with adhesive in addition to trowelling the adhesive onto the substrate.
- The final bed thickness of the adhesive should be at least 2mm for wall tiling and 3mm for floor tiling.
- Once the tiling is completed do not disturb the tiled surface for at least 2 hours at 23°C.

**COVERAGE:**

- 5-6m<sup>2</sup> using a 10mm notch

**EXPANSION / MOVEMENT JOINTS:**

- Movement joints to be installed as per AS3958

**GROUTING APPLICATION:**

- Grouting application can commence after adhesive has cured for 2 hours, or until the adhesive has hardened sufficiently that tiles are well fixed and will not be displaced during the grouting application
- Any adhesive that has leached into the grout joint must be raked out with a knife/spatula etc. prior to grouting
- For moisture sensitive stone installations, pre-test stone to ensure selected grout will not adversely affect the tile. Pre-seal stone as required and re-test before proceeding with grouting installation
- Refer to tile/stone manufacturers recommendations for suitable grout options
- Use [RLA LUMINOUS GROUT](#) or [RLA EPOXY GROUT](#) as per product installation recommendations
- Protect tiling from rain and inclement weather until 24 hours after grouting is complete.  
**\*Drying times may be extended in humid conditions and colder temperatures.**

**CLEAN UP:**

- Excess adhesive from the face of the tiles can be cleaned up with a damp cloth while the adhesive is still in a wet state
- Tools and other equipment can be cleaned using water while the adhesive is still wet.
- Dried adhesive to be removed by mechanical means

**PACKAGING:**

20kg Bags

**SHELF LIFE & STORAGE:**

- 12 months stored in original unopened packaging
- Best stored in a dry area at room temperature
- Keep off cold floors and out of direct sunlight

**HEALTH & SAFETY:**

For information and advice on the safe handling, first aid, storage and disposal of chemical products, users must refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

### **LIMITATIONS:**

- As natural stone can vary between batches and suppliers, RLA recommends consulting with the Stone supplier to determine the correct adhesive type, as well as trying a small area to assess the moisture sensitivity of the Stone
- Do not apply Stoneset when surface or ambient temperatures are above 35°C and below 5°C.
- Stoneset is not suitable for tiling over timber flooring.
- Not suitable for Class B or Class C moisture-sensitive stone including green marble and some limestone
- Not suitable for stone or conglomerate that is dimensionally unstable
- For detailed advice on applications not mentioned in this TDS, contact the RLA Technical Department

<b>TECHNICAL DATA:</b>	
<b>Colour</b>	White
<b>Bulk Density (kg/dm<sup>3</sup>)</b>	1.18
<b>Shelf life</b>	12 months
<b>Packaging</b>	20kg bags
<b>Coverage - 10mm notch</b>	5-6 m <sup>2</sup>
<b>APPLICATION DATA - 23°C AT 50% RH</b>	
<b>Note:</b> Ambient and surface temperatures, humidity, tile and surface porosity will vary dry times	
<b>Mixing Ratio</b>	5litres water per 20kg bag
<b>Open Time</b>	30 minutes
<b>Adjustment Time</b>	40 minutes
<b>Pot Life</b>	45 minutes
<b>Ready for Grouting</b>	2 hours
<b>Light Foot traffic</b>	3-4 hours
<b>Ready for wet area service</b>	3-4 days
<b>Ready for Immersion</b>	7 days
<b>PERFORMANCE (ISO 13007)</b>	
<b>Tensile adhesion strength after</b>	
<b>28 days</b>	≥2MPa
<b>Water immersion</b>	≥1MPa
<b>Freeze/thaw</b>	≥1MPa
<b>CLASSIFICATION</b>	<b>C2FTES1</b>

**WARRANTY STATEMENT:**

RLA Polymers guarantees this product against manufacturing defects and guarantees it to be manufactured to our published specification.

We certify that this product is suitable for use when fully cured and will perform as described in our technical data sheet or other published materials.

RLA Polymers will replace the product free of charge when purchased from any legally verifiable source and where a product is proven to have been stored, handled, and install according to instructions published on our packaging and within the stated shelf life. The Installation of all materials must be carried out in accordance The Installation of all materials must be carried out in accordance with relevant Australian Standards.

Warranty doesn't apply if damage, loss, failure to follow instructions, or other circumstances are out of our control.

Sufficient time and access to investigate any complaint must be accorded to RLA Polymers.

The consumer is responsible for any expenses incurred in making a claim.

A claim form can be requested by:

**PHONE:** 1800 242 931

**EMAIL:** [info@rlapolymers.com.au](mailto:info@rlapolymers.com.au)

**MAIL:** 215 Colchester Road Kilsyth Victoria 3137  
(Attention Customer Service)

**WEBSITE:** [www.rlapolymers.com.au](http://www.rlapolymers.com.au)

**AUSTRALIAN CONSUMER LAW:**

Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality, and the failure does not amount to a major failure. The benefits under our warranty are in addition to other rights and remedies available to the consumer under the law in relation to the goods and services to which the warranty relates.

**DISCLAIMER:**

All statements and technical information contained herein are based on tests we believe to be reliable, but the accuracy thereof is not guaranteed.

Users assume all risk and liability resulting from the use of the product and must confirm the suitability thereof by their own tests. Conditions of Sale contain a limited warranty against manufacturing defects.

Version: 01

Issue date: 01/04/2024

**RLA Polymers Pty Ltd** ACN 004 709 915

Head Office  
215 Colchester Road  
Kilsyth, Victoria, 3137  
Tel: 1800 242 931

New South Wales  
5A 246 Miller Road  
Villawood, NSW, 2163

Queensland  
57 Fulcrum Street  
Richlands, QLD, 4077

South Australia  
Unit 2/7 Berger Road  
Wingfield, SA, 5013

Western Australia  
24 Harwell Way  
Bassendean, W.A, 6054  
Tel: 08 9279 8911

For the latest product information please visit [rlapolymers.com.au](http://rlapolymers.com.au)